

PRODUCT RANGE OVERVIEW

•STANDARD GRADES

7233, 7033, 6333, 5533, MX 1940, 4033, MX 1205, 3533, 2533

•REINFORCED GRADES

RDG 314, RDG 277

•BREATHABLE AND ANTISTATIC GRADES

MV 1041, MV 1074, MV 3000, MV 6100, MH 1657, INIT 1100

•SOFTENING ADDITIVE FOR PA 6

MP 1878

•STABILIZATION

- SA grades: no additive for medical and food uses
- SN grades: UV stabilized
- SP grades: new generation UV stabilized

GENERAL CHARACTERISTICS

THERMOPLASTIC GRADES

CHARACTERISTICS	CONDITIONS	STANDARD	UNITS	RDG 314	RDG 277	7233	7033	6333	5533	MX 1940	4033	MX 1205	3533	2533
SHORE HARDNESS	instantaneous	ISO 868/ ASTM D 2240	Shore D	75	71	69	69	64	54	55	42	46	33	27
			Shore A	-	-	-	-	-	-	-	-	90	92	82
	after 15 seconds	ISO 868/ ASTM D 2240	Shore D	71	68	61	61	58	50	48	35	41	25	22
			Shore A	-	-	-	-	-	-	-	-	89	90	80
DENSITY		ISO 1183	g/cm ³	1.12	1.12	1.01	1.01	1.01	1.01	1.01	1.00	1.01	1.00	1.00
MELTING POINT		ISO 11357/ ASTM D 3418	°C	175	174	174	172	169	159	154	160	147	143.5	133.5
VICAT SOFTENING POINT	under 10 N	ISO 306/ ASTM D 1525	°C	173	170	164	164	157	142	127	131	111	77	58
WATER ABSORPTION AT EQUILIBRIUM	at 23°C and 50% RH	ISO 62/ ASTM D 570	%	0.6	0.6	0.7	0.7	0.7	0.6	0.7	0.5	0.4	0.4	0.4
WATER ABSORPTION SATURATION	24h in water at 23°C	ISO 62/ ASTM D 570	%	0.9	1.0	0.9	0.9	1.1	1.2	1.7	1.2	1.2	1.2	1.2
MELT INDEX	235°C / 1kg	ISO 1133/ ASTM D 1238	g/10 mn	-	-	4	6	5	7	-	5	9	8	10
LINEAR COEFFICIENT OF THERMAL EXPANSION	from - 40°C to +140°C	ASTM D 696	10 ⁻⁵ /°C	-	-	12	16	14	17	-	19.5	20	21	20
SURFACE RESISTIVITY		IEC 60093/ ASTM D 257	Ohm/sq	-	-	10 ¹²								
VOLUMIC RESISTIVITY			Ohm.cm	-	-									
FILLER			Glass fiber	-	-	-	-	-	-	-	-	-	-	-

PROPERTIES (RUBBER MATERIALS TESTS)

CHARACTERISTICS	CONDITIONS	STANDARD	EQUIVALENT	UNITS	7233	7033	6333	5533	4033	MX 1205	3533	2533		
TENSILE STRESS	to obtain extension of	v = 500 mm/min	ASTM D 638	MPa	10%	28.7	21.6	14.2	10	5.1	5.5	1.6	1.1	
					50%	25	21.8	16.6	13.2	8.9	9.1	4.6	3.2	
					100%	24.8	21.1	16.9	13.6	10.5	9.1	5.8	4.2	
TENSION SET	under	v = 500 mm/min	ISO 2285	ASTM D 412 (method A)	%	5%	0.8	0.5	0.5	0.5	0.4	0.5	0.4	0.4
						10%	2.4	1.9	1.5	1.5	1.2	1.2	0.7	0.5
						15%	4.2	3.8	3.3	2.9	2.1	2.3	0.9	0.8
						20%	6.6	5.8	5.1	4.6	3.1	3.3	1.4	0.9
TEAR RESISTANCE	unnotched	ISO 34-1	ASTM D 624	kN/m	194	177	147	135	116	115	78	66		
					notched	166	149	127	106	85	77	50	44	
TABER ABRASION RESISTANCE	H18 / load 1kg / 1000 rotations	ISO 9352		mm	54	59	60	62	62	60	77	99		
ABRASION RESISTANCE	10 N / 40 m	ISO 4649	DIN 53516	mm ³	-	-	55	47	48	40	64	130		
RESILIENCE		ISO 4662	DIN 53512		-	-	53	57	66	58	69	70		
COMPRESSION SET	under deformation of 25%	70h at 23°C	ISO 815	%	-	-	47	43	32	37	22	19		
COMPRESSION SET	under load of 9.3MPa	22h at 70°C	ASTM D 395 (method A)	%	-	-	5	10	21	-	54	62		
RESISTANCE TO CRACKING BY REPEATED FLEXURE	20 °C – 100 000 flex	ISO 133		mm	-	-	5	3	2	-	2	2		
					-20 °C – 50 000 flex	-	-	14	9	4.5	-	2.5	2.5	

PROPERTIES (PLASTIC MATERIALS TESTS)

CHARACTERISTICS	CONDITIONS	STANDARD	UNITS	RDG 314	RDG 277	7233	7033	6333	5533	MX 1940	4033	MX 1205	3533	2533
FLEXURAL MODULUS		ISO 178	MPa	2200	1500	513	390	285	170	167	77	86	21	12
		ASTM D 790	MPa	-	-	518	379	278	164	-	81	93	20	14
TENSILE MODULUS		ISO 527	MPa	-	-	522	384	280	161	-	71	81	18	10
		ASTM D 638	MPa	2600	2000	521	383	287	160	158	74	79	20	10
TENSILE – STRESS AT YIELD	v = 50 mm/min	ASTM D 638 type IV	MPa	62	50	26	22	18	12	12	-	-	-	-
TENSILE – STRAIN AT YIELD			%	6	10	18	20	22	25	25	-	-	-	-
TENSILE – STRESS AT BREAK			MPa	56	45	56	54	53	52	51	40	42	39	32
TENSILE – STRAIN AT BREAK			%	10	17	1300	1350	1350	1450	1550	1450	1550	1600	1750
IMPACT STRENGTH * (IZOD) AT + 23 °C	unnotched	ASTM D 256	J/m	-	-	1380 ^P	969 ^P	607 ^P	N	-	N	N	N	N
	notched		J/m	-	-	192 ^C	847 ^P	554 ^P	N	-	N	N	N	N
IMPACT STRENGTH * (IZOD) AT - 40 °C	unnotched	ASTM D 256	J/m	-	-	2460 ^P	2345 ^P	1589 ^P	1589 ^P	-	N	N	N	N
	notched		J/m	-	-	50 ^C	50 ^C	11 ^C	1038 ^P	-	N	N	N	N
IMPACT STRENGTH * (CHARPY) AT + 23 °C	unnotched	ISO 179	kJ/m ²	-	-	N	N	N	N	N	N	N	N	N
	notched		kJ/m ²	-	-	15 ^C	120 ^P	N	N	N	N	N	N	N
IMPACT STRENGTH * (CHARPY) AT - 30 °C	unnotched	ISO 179	kJ/m ²	-	-	N	N	N	N	N	N	N	N	N
	notched		kJ/m ²	7.3	7.3	10 ^C	10 ^C	20 ^C	N	N	N	N	N	N

* N: no break
P: partial break
C: complete break

GENERAL CHARACTERISTICS - SPECIAL GRADES

CHARACTERISTICS	CONDITIONS	STANDARD	EQUIVALENT	UNITS	ANTISTATIC		MV 1041	MP 1878	MV 3000	MV 6100	INIT 1100
					MH 1657	MV 1074					
SHORE HARDNESS	instantaneous	ISO 868	ASTM D 2240	Shore D	40	40	60	58	35	58	75
DENSITY		ISO 1183		g/cm ³	1.14	1.07	1.04	1.09	1.02	1.04	1.12
MELTING POINT		ISO 11357	ASTM D 3418	°C	204	158	170	195	158	170	198
VICAT SOFTENING POINT	under 10 N	ISO 306	ASTM D 1525	°C	160	-	-	169	-	-	-
FLEXURAL MODULUS	at 23°C and 50% RH	ISO 178	ASTM D 790	MPa	80	80	270	180	45	210	440
TENSILE – STRESS AT BREAK	v = 50 mm/min	ISO 527		MPa	32	30	44	60	35	48	71
TENSILE – STRAIN AT BREAK	v = 50 mm/min	ISO 527		%	1500	1700	450	550	500	-	1300
WATER ABSORPTION AT EQUILIBRIUM	at 23°C and 50% RH	ISO 62	ASTM D 570	%	4.5	1.4	0.9	1.35	1	0.9	-
WATER ABSORPTION SATURATION	24h in water at 23°C	ISO 62	ASTM D 570	%	120	48	12	6.7	28	11	-
MELT INDEX	235°C / 1kg	ISO 1133	ASTM D 1238	g/10 mn	27	14	7	8	-	-	1.7
SURFACE RESISTIVITY		IEC 60093	ASTM D 257	Ohm/sq	1 10 ⁹	3 10 ⁹	-	-	-	-	-
VOLUMIC RESISTIVITY				Ohm.cm	2 10 ⁹	2.5 10 ⁹	-	-	-	-	-

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See MSDS for Health & Safety Considerations

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.